

RESINTECH, INC.

INNOVATIONS IN ION EXCHANGE

160 Cooper Road, West Berlin, NJ 08091

TEL (856) 768-9600 FAX (856) 768-9601

FORM 303 AUTO

RESIN PERFORMANCE PREDICTIONS

PLEASE HAND TO:

Recipient or Project Manager

SAMPLE IDENTIFIER

1000

FAX NO:

856-768-9601

COMPANY :

Good Systems Inc.

PROJECT:

Name of project or Job site etc.

TYPE TWO GEL ANION RESIN COMPARISON**TEST RESULTS**

	This sample		New resin
Weak Base Capacity	0.4	meq/mL	< .1
Salt Splitting Capacity	0.8	meq/mL	> 1.4
Total Capacity	1.2	meq/mL	> 1.4

RELATIVE OPERATING CAPACITY COMPARED TO NEW RESIN